

WHAT IS CLAIMED IS:

1. A three-dimensional optical memory medium comprising:
a solid medium forming a base substrate of said optical
memory, said solid medium comprising luminescent ions having a
5 first valence; and
a plurality of spots which are three-dimensionally
distributed in said solid medium, said luminescent ions being
contained in said spots and having a second valence different from
said first valence as a result of condensing a pulsed laser beam in
10 said solid medium.
2. A three-dimensional optical memory medium according to
claim 1, wherein said spots are different from said solid medium in
emission wavelength and/or luminous intensity.
- 15 3. A three-dimensional optical memory medium according to
claim 1, wherein said luminescent ions contained in said solid
medium and said spots are rare earth element ions.
- 20 4. A three-dimensional optical memory medium according to
claim 1, wherein said spots are prepared by condensing the pulsed
laser beam in said solid medium to reduce said luminescent ions of
said solid medium from said first valence to said second valence.
- 25 5. A three-dimensional optical memory medium according to
claim 1, wherein said solid medium is made of an inorganic glass
comprising aluminum.
- 30 6. A three-dimensional optical memory medium according to
claim 3, wherein said rare earth element ions are ions of at least
one rare earth element selected from the group consisting of Ce, Pr,
Sm, Eu, Tb, Tm and Yb.

7. A three-dimensional optical memory medium according to claim 1, wherein said solid medium is made of a fluoride glass comprising (a) aluminum fluoride and (b) said luminescent ions that are trivalent Sm ions, and wherein said luminescent ions
5 contained in said spots are bivalent Sm ions.
8. A three-dimensional optical memory medium according to claim 1, wherein said pulsed laser beam has a wavelength that is different from an absorption wavelength of said solid medium.
- 10 9. A three-dimensional optical memory medium according to claim 1, wherein said pulsed laser beam has a peak power density of 10^8 – 10^{17} W/cm².
- 15 10. A three-dimensional optical memory medium according to claim 1, wherein said pulsed laser beam has a pulse width not greater than 10^{-10} seconds.
11. A process for producing a three-dimensional optical
20 memory medium, said process comprising:
(a) providing a solid medium comprising luminescent ions having a first valence;
(b) condensing a pulsed laser beam to a focal point in said solid medium such that a spot corresponding to said focal point is
25 formed in said solid medium, said spot comprising said luminescent ions having a second valence different from said first valence; and
(c) three-dimensionally scanning said solid medium with
said pulsed laser beam such that a plural number of said spot are
30 formed three-dimensionally in said solid medium, thereby producing said three-dimensional optical memory medium.
12. A process according to claim 11, wherein said luminescent

ions contained in said solid medium and said spots are rare earth element ions.

13. A process according to Claim 11, wherein said spots are
5 prepared by condensing the pulsed laser beam in said solid medium to reduce said luminescent ions of said solid medium from said first valence to said second valence.

14. A process according to Claim 11, wherein said solid
10 medium is made of an inorganic glass comprising aluminum.

15. A process according to claim 12, wherein said rare earth
element ions are ions of at least one rare earth element selected from the group consisting of Ce, Pr, Sm, Eu, Tb, Tm and Yb.

16. A process according to Claim 11, wherein said solid
medium is made of a fluoride glass comprising (a) aluminum
fluoride and (b) said luminescent ions that are trivalent Sm ions,
and wherein said luminescent ions contained in said spots are
20 bivalent Sm ions.

17. A process according to Claim 11, wherein said pulsed laser
beam has a wavelength that is different from an absorption
wavelength of said solid medium.

18. A process according to Claim 11, wherein said pulsed laser
beam has a peak power density of 10^8 - 10^{17} W/cm².

19. A process according to Claim 11, wherein said pulsed laser
30 beam has a pulse width not greater than 10^{-10} seconds.

20. A process for reading information from a
three-dimensional optical memory medium, said medium

comprising:

a solid medium forming a base substrate of said optical memory, said solid medium comprising luminescent ions having a first valence; and

5 a plurality of spots which are three-dimensionally distributed in said solid medium, said luminescent ions being contained in said spots and having a second valence different from said first valence as a result of condensing a pulsed laser beam in said solid medium, said process comprising:

10 irradiating said three-dimensional optical memory medium with a laser beam having a wavelength such that said luminescent ions contained in said spots are selectively excited and thereby emit light.